Listing of Claims

The following listing of claims will replace all prior versions, and listings, of claims in the subject application:

1. (currently amended) A phase-change type optical information recording medium comprising:

a transparent substrate; a first protective layer on the substrate; a recording layer on the first protective layer; a second protective layer on the recording layer; and a reflective layer on the second protective layer,

wherein the recording layer includes as a main component ~~$Ag_\alpha In_\beta Sb_\gamma Te_\delta$~~ $\underline{Ag_\alpha In_\beta Sb_\gamma Te_\delta}$ where α, β, γ, and δ represent atomic percents and satisfy the relations:

$0.1 \leq \alpha \leq 2.0$,

$3.0 \leq \beta \leq 8.0$,

$65.0 \leq \gamma \leq 75.0$,

$15.0 \leq \delta \leq 30.0$, and

$97 \leq \alpha + \beta + \gamma + \delta \leq 100$; and

wherein assuming that a minimum recording linear velocity to be V_1, a maximum recording linear velocity to be V_2, and a degree of modulation at the time of reading out information to be $I(V)$, then a value of $I(V_2)/I(V_1)$ is within a range from 1 to 1.2.

2. (original) The phase-change type optical information recording medium according to claim 1, wherein a ratio between the maximum recording linear velocity V_2 and the minimum

recording linear velocity V_1 is $V_2/V_1 \geq 2.5$.

3.   (original)   The phase-change type optical information recording medium according to claim 1, wherein the minimum recording linear velocity V_1 is 4.8 m/s or more.

4.   (original)   The phase-change type optical information recording medium according to claim 3, wherein the maximum recording linear velocity V_2 is 12.0 m/s or more.

Claim 5 (canceled).

6.   (previously presented)   The phase-change type optical information recording medium according to claim 1, wherein the AgInSbTe further contains nitrogen.

7.   (previously presented)   The phase-change type optical information recording medium according to claim 1, wherein a thickness of the recording layer is in a range from 13 nm to 23 nm.

8.   (currently amended)   A phase-change type optical information recording medium comprising at least one recording layer which records information based on crystalline-to-crystalline or crystalline-to-amorphous transition,

the phase-change type optical information recording medium

being rotated around a center of rotation when recording information in or reading information from said recording layer,

wherein the recording layer includes as a main component ~~AgαInβSbγTeδ~~ Ag$_\alpha$In$_\beta$Sb$_\gamma$Te$_\delta$ where α, β, γ, and δ represent atomic percents and satisfy the relations:

$0.1 \leq \alpha \leq 2.0$,

$3.0 \leq \beta \leq 8.0$,

$65.0 \leq \gamma \leq 75.0$,

$15.0 \leq \delta \leq 30.0$, and

$97 \leq \alpha + \beta + \gamma + \delta \leq 100$; and

wherein when the minimum and maximum linear velocities of rotation are respectively V_1 and V_2, then a value of a degree of modulation corresponding to the maximum linear velocity $I(V_2)$ divided by a degree of modulation corresponding to the maximum linear velocity $I(V_1)$ is between 1 and 1.2.

9.   (previously presented) The phase-change type optical information recording medium according to claim 8, wherein a ratio between the maximum recording linear velocity V_2 and the minimum recording linear velocity V_1 is $V_2/V_1 \geq 2.5$.

10.   (previously presented) The phase-change type optical information recording medium according to claim 8, wherein the minimum recording linear velocity V_1 is 4.8 m/s or more.

11.   (previously presented) The phase-change type optical

information recording medium according to claim 10, wherein the

maximum recording linear velocity V_2 is 12.0 m/s or more.

12.   (previously presented)   The phase-change type optical

information recording medium according to claim 8, wherein the

AgInSbTe further contains nitrogen.

13.   (previously presented)   The phase-change type optical

information recording medium according to claim 8, wherein a

thickness of the recording layer is in a range from 13 nm to 23

nm.